



OC SAFE NANOTECHNOLOGIES
YACHT PAINTS

CLASSICA

ANTIFOULING SELF- POLISHING COPOLYMER INTERMEDIATE

CODE: ESC...

DESCRIPTION

CLASSICA IS AN ANTIFOULING PARTIALLY SOLUBLE AND IS VERY EFFECTIVE IN BOTH SALT WATER AND BRACKISH WATER. IT IS USED ON EVERY TYPE OF BOAT, SAIL AND MOTOR. EFFECTIVE AT ALL SPEEDS, IS ALSO SUITABLE FOR SAILING BOATS FREQUENTLY AND FOR LONG PERIODS. CLASSICA IS A PRODUCT WITH A LOT OF EXPERIENCE AND TRACK RECORD BEHIND ALLOWING THIS PRODUCT, THE PRODUCT OF EXCELLENCE IN THE WIDE RANGE OF ANTIFOULINGS OF SAFE NANOTECHNOLOGIES.

INFORMATION

FUORI POLVERE DUST FREE 20 MIN	IMMERSIONE SPLASHING 24 H	RESA SPREADING 12M ² /LT	UGELLI TIPS 0,019- 0,023	DILUIZIONE THINNING DILUENTE 01			
--------------------------------------	---------------------------------	---	-----------------------------------	--	--	--	--

TECHNICAL DATA

TYPE	SINGLE COMPONENT
COLOR	RED - MIDNIGHT BLUE- BLACK - LIGHT BLUE - EXTRAWITHE
ASPECT	MAT
DENSITY	1.55±0.05 G/CM ³ MIDNIGHT BLUE - BLACK - LIGHT BLUE - EXTRAWITHE
SOLID CONTENT	1.72±0.05 G/CM ³ RED
MIX RATIO	69% VOL MIDNIGHT BLUE- BLACK - LIGHT BLUE - EXTRAWITHE
SANDING	66% VOL RED
COVERING LONG-TERM	NA (SINGLE COMPONENT)
SPREADING	~12 MQ/LT A 50 MIC.
COMPATIBILITY ON ALUMINIUM	DILUENTE 01
THINNER	2 YEARS

DRYING INFORMATION (T 20°C)

DUST FREE	20 MIN
SPASHING	24 H

MINIMUM DRY FILM THICKNESS PER COAT

100 MICRON

APPLICATION METHOD

THINNER	10%	15%	10%-15%

GENERAL INFORMATION

DO NOT EXPOSE TO HEAT SOURCES AND UNDER THE SUN. FOR BEST PRESERVATION OF **CLASSICA** BE SURE THAT WHEN STOCKED THE CANS ARE WELL CLOSED AND THE TEMPERATURE IS BETWEEN 5°C/40°F AND 35°C/95°F.

TRANSPORTATION

CLASSICA MUST BE KEPT IN CLOSED CANS AND DRUMS DURING TRANSPORTATION.

DESCRIPTIONS FOR USE

CAREFULLY MIX THE PRODUCT BEFORE USE. THE TECHNICAL DATA ARE DETERMINED AT 20° C UNLESS OTHERWISE DESIGNATION AND REFER TO THE PRODUCT READY FOR USE AND UNDILUTED.

GENERAL

ALWAYS READ THE TECHNICAL AND SAFETY ADVICES REPORTED ON LABELS. OBTAIN FURTHER SAFETY AND TECHNICAL ADVICE FROM OUR TECHNICAL SUPPORT. DISPOSAL: DO NOT DESPOSE THE EMPTY CANS OR RESIDUES OF PAINT IN THE ENVIRONMENT; USE ADEQUATE DISPOSAL CONTAINERS. IT IS PREFERRED TO DISPOSE THE PAINT RESIDUES WHEN ARE IN SOLID STATE. RESIDUES OF **CLASSICA** CANNOT BE DESPOSED AS NORMAL WASTE BUT ONLY AS SPECIAL DANGEROUS WASTE. THE DISPOSAL MUST BE DONE FOLLOWING THE LOCAL REGULATIONS ABOUT DANGEROUS WASTE. CONSULT LOCAL AUTHORITIES FOR ADVICE.

IMPORTANT NOTES

THE INFORMATION CONTAINED IN THIS TDS MUST NOT CONSIDERED EXHAUSTIVE. ANY USE WITHOUT WRITTEN AND CERTIFIED ADVICE FROM SAFE NANOTECHNOLOGIES TECHNICAL SUPPORT DOES IT AT HIS OWN RISK AND DANGER. IN THIS CASE SAFE NANOTECHNOLOGIES DOES NOT TAKE ANY RESPONSABILITY FOR THE COATING PERFORMANCE AND ANY DAMAGE DERIVING FROM SUCH UNCORRECT USE OF THE PRODUCT APART WHEN IT IS PROVEN THAT THE DAMAGES ARE DUE TO OUR NEGLIGENCE. THE INFORMATION CONTAINED IN THIS SHEET COULD BE SUBJECT TO MODIFICATION DUE TO OUR IMPROVED EXPERIENCE AND TO OUR POLITHICS OF PRODUCT DEVELOPMENTS.